

[Loctite® Hysol® Hot Melt Adhesives Properties Chart]

LOCTITE® PRODUCT	ITEM NUMBER	PACKAGE TYPE & SIZE	COLOR	VISCOSITY (cP) AT DISPENSE TEMPERATURE	TENSILE STRENGTH (psi)	OPEN TIME	TEMPERATURE RESISTANCE	% ELONGATION	HARDNESS (SHORE A)	AGENCY APPROVALS
LOCTITE® HYSOL® HOT MELT ADHESIVES	1942™ HYSOL®	83266 5 lb. sample bag pellets 83267 40 lb. carton pellets 83269 Maxistick™ 35 lb. carton 83271 PT™ stick 36 lb. carton 83272 Ministick™ 35 lb. carton 83273 5 oz. sample bag 83274 Superstick™ 10 in. 25 lb. bag 83275 Superstick™ 4 in. 25 lb. carton 83276 12 oz. sample bag 83277 Polyshot™ 35 lb. Carton	Tan	5,000	250	30 seconds	142°F	500	N/A	FDA CFR175,105
	7809FR™ HYSOL®	83390 Superstick™ 13 oz. bag 83391 Polyshot™ 13 oz. bag 83675 Superstick™ 32 lb. carton 83676 Polyshot™ 25 lb. pail	Amber	7,000	363	35 seconds	240°F	373	85	UL Classified for U.S.
	7811™ HYSOL®	83337 5 lb. sample bag pellets 83339 Polyshot™ 13 oz. sample bag 83340 Polyshot™ 25 lb. pail 83338 40 lb. carton pellets	Amber	6,400	400	35 seconds	266°F	1,200	N/A	N/A
	7901™ HYSOL®	83343 Polyshot™ 13 oz. sample bag 83342 40 lb. carton pellets 83344 Polyshot™ 25 lb. pail	Amber	750	260	35 seconds	300°F	80	84	N/A